



China

Choose certainty.  
Add value.

## TEST REPORT

No. : SHAM20160200643

Date : Feb.24,2016

Page : 1 of 2

NATIONAL QUALITY SUPERVISION AND INSPECTION CENTER ON INDUSTRIAL AND MINING  
ELECTRIC DRIVE VEHICLE

NO.11 EAST BAISHI ROAD, XIANGTAN JIUHUA ECONOMIC AND TECHNOLOGICAL  
DEVELOPMENT ZONE

The following sample(s) was/ were submitted and identified on behalf of the client as:

Sample Name : Metal test block  
Sample Number : SHAM20160200643  
Product or Lot No. : KOM 1  
Material and Mark : 35CrMo  
Test Required : Hardness test  
Date of Receipt : Feb.23,2016  
Test Period : Feb.23,2016~Feb.24,2016  
Test result(s) : For further details, please refer to the following page(s)

\*\*\*\*\* To be continued\*\*\*\*\*

Sign for  
TÜV SÜD Certification and Testing (China) Co., Ltd.  
Shanghai Branch  
Material Lab  
Reviewed by:

Ying Zhang

Ying Zhang  
Senior Testing Engineer



Authorized by:

Cosmo Yuan

Cosmo Yuan  
Technical Supervisor

Note: (1) General Terms & Conditions as mentioned overleaf. (2) The results exclusively relate to the sample(s) under test. (3) The test report shall not be reproduced except in full, without the written approval of the laboratory.

Laboratory:

Material Laboratory

The 3rd Building, No. 589, Quwu Road, Minhang District,  
Shanghai, 200241, P.R. China

Phone: +86 21 60149880

Fax: +86 21 60149870

www.tuv-sud.cn

Regd. Office:

TÜV SÜD Certification and Testing (China) Co., Ltd.

Shanghai Branch

3-13F, No.151 Heng Tong Road Shanghai 200070

P.R. China

TUV® SHAMI 0041250



China

Choose certainty.  
Add value.

## TEST REPORT

No. : SHAM20160200643

Date : Feb.24,2016

Page : 2 of 2

Hardness test:

Environment condition : Temperature 21°C, Humidity 40%RH

Test equipment : Number Metal-009, Model MHV-30Z

Test method : GB/T 4340.1-2009

Test result(s) :

Test item	Test position	Result		
HV10	1	288	285	289
	2	265	268	269
	3	255	257	254
	4	232	236	237

Sample photo(s):



This report is English version of test report SHAM20160200643, which exists in two official versions, English version and Chinese version.

\*\*\*\*\* End of report \*\*\*\*\*

Note: (1) General Terms & Conditions as mentioned overleaf. (2) The results exclusively relate to the sample(s) under test. (3) The test report shall not be reproduced except in full, without the written approval of the laboratory.

Laboratory:

Material Laboratory

The 3rd Building, No. 589, Quwu Road, Minhang District,  
Shanghai, 200241, P.R. China

Phone: +86 21 60149880

Fax: +86 21 60149870

www.tuv-sud.cn

Regd. Office:

TÜV SÜD Certification and Testing (China) Co., Ltd.

Shanghai Branch

3-13F, No.151 Heng Tong Road Shanghai 200070

P.R. China

TÜV<sup>®</sup> SHAML 0041249