

Test Report

Report Number: 1667007SHJ-MT-1

Applicant Name: National Quality Supervision and Inspection Report Date: 2016-03-11

Center on Industrial and Mining Electric Drive Vehicle

Applicant Address: No.11 East Baishi Road, Xiangtan Jiu Hua
Economic and Technological Development Zone.

Attn: Zeng Liying

Sample Description:

Product: Steel Plate

Model: /

Samples Quantity: Refer to the following report with detail information

Sample ID: IAS1667007-1

Date Received: 2016-03-09

Date Test Conducted: 2016-03-09~2016-03-11

Test address different from lab address (if existed) : Reference to report

Tests Conducted:


As requested by the applicant, for details refer to attached page(s).

Conclusion:


Section No.	Test Name	Evaluation
1667007SHJ-MT-1.001	Hardness Test	<input checked="" type="checkbox"/> Not Evaluated

Should you have any queries about the test report, please contact:


Approved by:

Name Jason Xiang
Title Manager

Checked by:

Name Kingsley Zhang
Title Reviewer

Prepared by:

Name Jiali Wang
Title Project Engineer

Test Report

Report Number: 1667007SHJ-MT-1

Test Items, Method and Results:

1667007SHJ-MT-1.001		Hardness Test			
Ref. Specs Section	GB/T230.1-2009				
Date Tested	2016-03-10				
Sample No.	IAS1667007-1				
Test Method	GB/T230.1-2009				
Acceptance Criteria	None				
Deviation	None				
Test Results	Sample ID	Hardness(HRB)			Evaluation
	IAS1667007-1 I	66.6	66.6	66.8	Not Evaluated
	IAS1667007-1 II	72.8	73.2	72.6	Not Evaluated
	IAS1667007-1 III	68.8	68.5	68.6	Not Evaluated
	IAS1667007-1 IV	68.0	67.8	68.1	Not Evaluated
Test Instruments	Equipment No.	Equipment Name		Calibration Due Date	
	MCLS019	Rockwell hardness tester		2016-10-14	
<u>Observations & Remarks</u>					
None					
<u>Pictures</u>					

Test Report

Report Number: 1667007SHJ-MT-1



Test sample

The End of Report

This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Only the Client is authorized to permit copying or distribution of this report and then only in its entirety. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. The observations and test results in this report are relevant only to the sample tested. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.